

PRINCCIPAL PROPERTIES

Product Category	PA6	Grade	TLZN01F	
测试标准	CB	ASTM	Unit	Typical value
Mechanical property				
Tensile strength at break	GB/T 1040-92	D638	Mpa	65
Elongation at break	GB/T 1040-92	D638	%	10
Yield flexural strength	GB 9341-88	D790	Mpa	120
Unnotched impact strength of tube-supported beam	GB/T 1043-93	D256	KJ/m ²	48
Notch impact strength of tube support beam	GB/T 1043-93	D256	KJ/m ²	8.5
Notched Izod Impact Strength	GB1843-89	D256	KJ/m ²	9
Rockwell hardness	GB9342-88			
Thermal property				
Heat distortion temperature	GB1643-89	D648	℃	75
Flame retardancy				V0
Processing				
Solution flow rate	GB3682-89	D1238	g/10min	5.2
Molding shrinkage			%	0.5~0.9
Injection molding temperature			℃	220~250
Density	GB1033-86	D792	g/cm ³	1.2

Note: The above data are typical values and are for reference only.