

PRINCCIPAL PROPERTIES

Product Category	PP	Grade	TLZP01F	
Standard test	CB	ASTM	Unit	Typical value
Mechanical property				
Tensile strength at break	GB/T 1040-92	D638	Mpa	28
Elongation at break	GB/T 1040-92	D638	%	50
Yield flexural strength	GB 9341-88	D790	Mpa	45
Unnotched impact strength of tube-supported beam	GB/T 1043-93	D256	KJ/m ²	40
Notch impact strength of tube support beam	GB/T 1043-93	D256	KJ/m ²	5
Notched Izod Impact Strength	GB1843-89	D256	KJ/m ²	6
Rockwell hardness	GB9342-88			
Thermal property				
Heat distortion temperature	GB1643-89	D648	℃	115
Flame retardancy				V0
Processing				
Solution flow rate	GB3682-89	D1238	g/10min	4.8
Molding shrinkage			%	1.5~1.7
Injection molding temperature			℃	180~220
Density	GB1033-86	D792	g/cm ³	1.12

Note: The above data are typical values and are for reference only.